



CELENIT NB

Technical data sheet



Thermal and acoustic insulation board, consisting of mineralized fir wood wool bound with white Portland cement. Wood wool is 3 mm wide. High quality boards for design acoustic absorption systems. It complies with EN 13168 and EN 13964 standards. The boards are certified by ANAB-ICEA and natureplus for eco-compatibility of materials and manufacturing process. CELENIT NB is PEFC™ certified. Also available with FSC® certification.

Edges detail

D - DT - T

Colours

natural or painted

Applications

false ceilings, wall coverings, baffles and acoustic rafts, design solutions

Technical data

Standard	EN 13168 - EN 13964				CE
Designation code	WW-EN13168-L3-W2-T2-S2-CS(10)200-CI3 (thicknesses 15-40 mm) WW-EN13168-L3-W2-T2-S2-CS(10)150-CI3 (thickness 50 mm)				
Length x Width [mm]	2400x600 - 2000x600 - 1200x600 - 600x600				
Thickness [mm]	15	25	35	50	
Weight [kg/m ²]	8.0	11.5	14.0	18.0	
Declared thermal conductivity λ_D [W/mK]	0.065				
Declared thermal resistance R_D [m ² K/W]	0.20	0.35	0.50	0.75	
Compressive stress at 10% deformation σ_{10} [kPa]	≥ 200 (thicknesses 15-40 mm) ≥ 150 (thickness 50 mm)		Durability		Class C
Water vapour transmission μ	5		Light reflection CELENIT ABE [%]		50.7 - 74.0 (painted white 05/15)
Specific heat c_p [kJ/kgK] ¹	1.81		Release of formaldehyde		Class E1
Reaction to fire ²	Euroclass B-s1, d0		Release of asbestos		it does not contain asbestos
Chloride content	≤ 0.06				

¹ Certified by the University of Bologna - LEBSC no. 809 | rev. 07.05.2009

² The reaction to fire does not change for painted products

Logistic data

Dimensions [mm]	Pallet	15 mm	25 mm	35 mm	50 mm
boards: 2400x600	boards per pallet	130	88	60	44
pallet: 2400x1200	m ² per pallet	187.20	126.72	86.40	63.36
boards: 2000x600	boards per pallet	130	88	60	44
pallet: 2000x1200	m ² per pallet	156.00	105.60	72.00	52.80
boards: 1200x600	boards per pallet	130	88	60	44
pallet: 1200x1200	m ² per pallet	93.60	63.36	43.20	31.68
boards: 600x600	boards per pallet	260	176	120	
pallet: 1200x1200	m ² per pallet	93.60	63.36	43.20	

Certifications

ISO 9001:2015 no. 1351
ANAB no. EDIL 2009_004
NATUREPLUS no. 1007-1511-134-1
EPD® S-P-00477
FSC® no. ICILA-COC-002789
PEFC™ no. ICILA-PEFCCOC-000117
ICEA no. LEED 2015_001
ICEA no. REC 2015_001





Storage, use and maintenance

The boards must be stored on a pallet placed on a flat surface, protected from rain and direct sunlight. Pallets must be handled with care on site. Bumping the corners of the pallets can cause damage to the boards. For more information see the "Storage, use and maintenance" information available in the download area of the website www.celenit.com.



CELENIT boards are dimensionally stable (EN 13168), however, they must be installed after acclimating to the same room they are going to be installed in, as well as after all concrete works are finished and the doors, windows, heating and ventilation systems have been installed. Room temperature must be kept constant before and after installation. Do not suddenly change the temperature of the room after installation.

The boards have one side that should be visible (front of the board) and another side that should be placed against the structure (back of the board). The back of the board usually has the CELENIT logo or shows calibration marks. The front may be painted and/or has worked edges. In the absence of paint or edges, the front can be identified according to the pallet layout: the front of the boards faces the top and the back faces the pallet.

Due to their natural production process and raw materials, boards that are not painted may have an uneven color. The boards must be painted to have an even color.